

FABRIC SPECIFICATIONS

CONTENT	100% POLYESTER
WEIGHT	16 OZ/LIN YD
ENDS/PICKS	17/16 PER INCH
WIDTH	66"
ORIGIN	CANADA

PERFORMANCE CHARACTERISTICS

TENSILE STRENGTH ASTM D1682	WARP: 205.0 LBS. FILL: 185.0 LBS.
TEAR STRENGTH ASTM D2261	WARP: 40.0 LBS. FILL: 50.0 LBS.
MOISTURE REGAIN ASTM D2654	0.5% MAX
COLORFASTNESS TO LIGHT AATCC 16A	40 HRS.

FLAMMABILITY

ASTM E-84 (TUNNEL TEST)	CLASS A OR 1
CALIFORNIA TECHNICAL BULLETIN 117 SECTION E (CS-191-53)	PASSES
NFPA 701	PASSES
UL TEST #214	PASSES
CAN/ULC-S102	PASSES
UL 723	PASSES

RECOMMENDED CLEANING CARE

W-S	WATER-BASED CLEANING AGENTS AND FOAM MAY BE USED FOR CLEANING. THIS FABRIC MAY ALSO BE CLEANED WITH MILD, WATER-FREE SOLVENTS. CLEANING BY A PROFESSIONAL CLEANING SERVICE IS RECOMMENDED.
------------	--

VARIATIONS IN COLOR AND TEXTURE ARE INHERENT TO THIS TEXTILE.
APPLICATION TESTING OF THIS PRODUCT IS RECOMMENDED.



U.L. RECOGNIZED COMPONENT: THIS FABRIC CAN BE APPLIED WITHOUT NEED FOR FURTHER TESTING TO ANY OFFICE PANEL SYSTEM WHICH HAS BEEN AUTHORIZED FOR USE WITH FABRICS INCLUDED IN UL'S FABRIC RECOGNITION PROGRAM.



OEM ORIGINAL: THIS PRODUCT IS THE VERTICAL SURFACE FABRIC UTILIZED ON SYSTEMS PRODUCED BY LEADING ORIGINAL EQUIPMENT MANUFACTURERS.